



DOW CORNING® 340 Heat sink compound

FEATURES

- High thermal conductivity
- Low bleed
- Non-sag

Non-curing silicone compound

APPLICATIONS

- Designed to provide a long term thermal bridge between power components and heat sinks.
- Typical applications include: thermally connecting transistors and thyristors to heat sinks.

TYPICAL PROPERTIES

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

CTM*	ASTM*	Property	Unit	Value
As supplied				
0176		Colour		White
0191	D217	Consistency - penetration, worked (60) and measured within 1 minute after working	mm/10	260
0033		Bleed, 24 hours at 200°C	%	Nil
0033		Evaporation, 24 hours at 200°C	%	0.35
0097	D1475	Specific gravity		2.2
0069		Thermal conductivity	W/m.K	0.55

* CTM: Corporate Test Method, copies of CTMs are available on request.
ASTM: American Society for Testing and Materials.

HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LOCAL DOW CORNING SALES REPRESENTATIVE.

USABLE LIFE AND STORAGE

When stored at or below 38°C in the original unopened containers, this product has a usable life of 60 months

from the date of production.

PACKAGING

This product is available in standard industrial container sizes. For details please refer to your Dow Corning sales office.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship

organization and a team of Health, Environment and Regulatory Affairs specialists available in each area.

For further information, please consult your local Dow Corning representative.

**WARRANTY
INFORMATION - PLEASE
READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Dow Corning specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless Dow Corning provides you with a specific, duly signed endorsement of fitness for use, Dow Corning disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.