

Ver:	Α
DATE:	2019-03-22
D00 N	U.D. 405500D

DOC No:JLD-105568P

Specification Approval Sheet

Model Name : 105568P

Description : 3.7V/5000mAh

Manufacturer : FUL-ENERGY

Version : 2.0

Date : 22/03/2019



Manufactory Sign:

Prepared	Checked	Approved 批准
徐工	徐工	袁总工

Customer Approved:

Prepared 制作	Checked 检验	Approved 批准
徐工	袁总工	袁总工



Ver:		Α
		2019-03-22
DOC N	lo:	JLD-105568P

1 Scope

This specification is applies to describe the related Battery product in this Specification and the Battery/cell supplied by Ful-Energy Co., Ltd only.

2 Model: 105570P

3 Cell Specification

No.	Items	Specifications		
				Remark
1	Nominal Capacity	5000mAh		0.2C Standard
2	Minimum Capacity	4950	lmAh	discharge 0.2C
3	Nominal Voltage	3.7	7V	Mean Operation Voltage
4	Delivery voltage	3.7~	3.9V	Within 10 days from Factory
5	Charge Voltage	4.2V±0.03V		By standard charge method
6	Standard charging method	0.2C constant current,4.2V constant voltage charge to 4.2V,continue charging till current deline to ≤0.01C		0.2C - 4.2V ≤0.01C, 4.0h(
7	7 Charge current	0.2C	1000mA	Standard charge, charge time:4.0h(Ref) 4.5h
/		0.5C	2500mA	Rapid Charge, charge time:3.0h(Ref)
8	Standard discharging method	0.2C constant current discharge to 2.75V,		0.2C 2.75V
9	Cell Internal Impedance	≪40		Internal resistance measured at AC 1KH _z after 50% charge



Ver: A

DATE: 2019-03-22

DOC No:JLD-105568P

3 Cell Specification / Continuous

No.	Items	Specifications		Remark
10	Maximum charge current	2500mA		For continuous charging mod
11	Maximum discharge current	2500	0mA	For continuous discharge mod
12	Operation Temperature and relative	Charge	0~45℃ 60±25%R.H.	Charge at a very low temperature such as blew 0°C,will be get a lower capacity and
12	humidity Range	Discharge	-10~60℃ 60±25%R.H.	reduce cycle life of the battey
13	Storage temperature for a long time	-20~25℃ 60±25%R.H.		Do not storage exceed half year.Must charge once when storage for half year.Must charge the battey which with protect circuit when storage for three mouthes.



Ver:		Α
DATE:		2019-03-22
DOC	No	o:JLD-105568P

4 Battery/Cell performance test Criteria

4.1 Appearance inspection by visual

There shall be no such defect as flaw, crack, rust, leakage, which may adversely affect commercial value of battery.

4.2 Environmental test condition

Unless otherwise specified, all test stated in this product specification are conduct at below test condition

Temperature: 20°C~25°C

Relatiive Humidity: $60\% \pm 25\%$ R.H.

4.3 Cell Electrical characteristics

No	I tems	Test Method and Condition	Criteria	
	Rated Capacity at 0.2C(Min.) 0.2C	After standard charge,the capacity shall be measured on 0.2C discharge till the voltage discharge to 2.75V,	≥5000mAh ≥1	100%
1	Rated Capacity at 1C(Min.) 0.5C	After standard charge,the capacity shall be measured on 0.5C discharge till the voltage discharge to 2.75V	≥4950mAh >	99%
2	Cycle Life	Charging and discharging battey as blew conditions 0.2C standard charge to 4.2V end-off 0.2C standard discharge to 2.75V cut-off Continuous charge and discharge for 500 cycles,the capacity will be measure after the 500th cycle	≽70% of initial capacity	
3	Capacity retention	The battery to be charge in accordance whith standard charge condition at 20~25℃, then storage the battery at an ambient temperature 20~25℃ for 28 days. Measure the capacity after 30 days with 0.2C at 20~25℃ as retention capacity	Retention capacity ≥85%	



Ver:	A
DATE:	2019-03-22

DOC No:JLD-105568P

4.4 Mechanical characteristics

No	Items	Test Method and Condition	Criteria
1	Free fall test	The battery to be fully charged in accordance with stnadard charge condition, then drop the battery three times from a height of 1,0 m onto a concrete floor. The batteries are dropped so as to obtain impacts in random orientations.	No Fire,
2	Vibration test	After standard charging, fixed the cell to vibration table and subjected to vibration cycling that the frequency is to be varied at the rate of 1Hz per minute between 10Hz and 55Hz, the excursion of the vibration is 1.6mm. The cell shall be vibrated for 30 minutes per axis of XYZ axes.	No explosion,No leakage,No fire
3	Crush test	Fully charged the battery in accordance with standard charge condition, the battery is to be crushed between two flat plates. Continuous to applied force on battery of 13kN(17.2Mpa),stopped until a pressure reading of 17.2Mpa is reached on the hydraulic ram	No explosion, No fire
4	Shock test	The fully charged battery is secured to the testing machine by means of a rigidmount which will support all mounting surfaces of the cell or battery. The battery is subjected to a total of three shocks of equal magnitude. The shocks are applied in each of three mutually perpendicular directions. At least one of them shall be perpendicular to a flat face. For each shock the cell or battery is accelerated in such a manner that during the initial 3 milliseconds the minimum average acceleration is 75 gn. The peak acceleration shall be between 125 gn and 175 gn. Cells or batteries are tested in an ambient temperature of 20~25°C	No explosion,No leakage,No fire



Ver: A

DATE: 2019-03-22

DOC No:JLD-105568P

4.5 Safty performance


No	Items	Test Method and Condition Crite	ria
1	Thermal exposure test	Each fully charged cell, stabilized at room temperature, is placed in a circulating air-convection oven. The oven temperature is raised at a rate of 5 °C/min ± 2 °C/min to a temperature of 130 °C ± 2 °C. The cell remains at this temperature for 10 min before the test is discontinued.	No explosion,No fire
2	Low pressure	Each fully charged cell is placed in a vacuum chamber, in an ambient temperature of 20~25°C. Once the chamber has been sealed, its internal pressure is gradually reduced to a pressure equal to or less than 11,6 kPa (this simulates an altitude of 15240 m) held at that value for 6 h.	No explosion,No leakage,No fire
3.	Short test	The fully charged battery is to be short-circuited by connecting the positive and negative terminals of the battery with resistance load not exceed 100m Ω .Tests are to be conducted at room temperature $20~25$ °C.	No explosion,No fire The Temperature of the Battery surface not exceeded than 150℃
4	Forced discharge test	A discharged cell is subjected to a reverse charge at 1c for 90 min.	No explosion,No fire
5	Over charge test	After standard charge, continue to charge with a constant voltage 4.6V per a cell, holding 8h.	No explosion, No fire, No leakage
6	Soak Test	Put the batteries into clean water, be soaked for 24 hours.	No break, No fire



Ver:	Α
DATE:	2019-03-22

DOC No:JLD-105568P

5 Cell initial Dimensions



NO	Items	Units:mm	Remark
1	Thinkness	1.0±0.3	Max.
2	Width/	55±0.3	Max.
3	Height	68±0.3	Max.
4	L1	26±2	
5	L2	8±2	
6	L3	5±0.1	

Drawed	Checked	Approved



Ver:	Α
DATE:	2019-03-22
DOC No	:JLD-105568P

6. Handling of Cells

- 6.1 Consideration of strength of film package
 - 1) Soft Aluminium foil

Easily damaged by sharp edge parts such as pins and needles, Ni-tabs, so don't strike by those sharp parts.

2)Sealed edge may be damaged by heat above 100°C, bend or fold sealed edge.

6.2 Prohibition short circuit

Never make short circuit cell. It generates very high current which causes heating of the cells and may cause electrolyte leakage, gassing or explosion that are very dangerous.

The LIP tabs may be easily short-circuited by putting them on conductive surface.

Such outer short circuit may lead to heat generation and damage of the cell.

An appropriate circuitry with PCM shall be employed to protect accidental short circuit of the battery pack.

6.3.Mechanical shock

LIP cells have less mechanical endurance than metal-can-cased LIB.

Falling, hitting, bending, etc. may cause degradation of LIP characteristics.

6.4 Handling of tabs

The battery tabs are not so stubborn especially for aluminum tab.

Don't bend tab.

Do not bend tabs unnecessarily.

7. Notice for Designing Battery Pack

7.1 Pack toughness

Battery pack should have sufficient strength and the LIP cell inside should be protected from mechanical shocks.

7.2 Cell fixing

The LIP cell should be fixed to the battery pack by its large surface area.

No cell movement in the battery pack should be allowed.

7.3 Inside design

No sharp edge components should be insides the pack containing the LIP cell.

7.4 Tab connection

Ultrasonic welding or spot welding is recommended for LIP tab connection method.

Battery pack should be designed that shear force are not applied to the LIP tabs.

If apply manual solder method to connect tab with PCM, below notice is very important to ensure battery performance:

- 1) The solder iron should be temperature controlled and ESD safe;
- 2) Soldering temperature should not exceed 350°C;
- 3) Soldering time should not be longer than 3s;



Ver:	Α
DATE:	2019-03-22

DOC No:JLD-105568P

- 4) Soldering times should not exceed 5 times, Keep battery tab cold down before next time soldering;
- 5) Directly heat cell body is strictly prohibited, Battery may be damaged by heat above approx. 100°C

7.5 For mishaps

Battery pack should be designed not to generate heat even when leakage occurs due to mishaps.

- 1) Isolate PCM (Protection Circuit Module) from leaked electrolyte as perfectly as possible.
- 2) Avoid narrow spacing between bare circuit patterns with different voltage. (Including around connector)

LIP battery should not have liquid from electrolyte, but in case If leaked electrolyte touch bare circuit patterns, higher potential terminal material may dissolve and precipitate at the lower potential terminal, and may cause short circuit. The design of the PCM must have this covered.

8. otice for Assembling Battery Pack

Shocks, high temperature, or contacts of sharp edge components should not be allowed in battery pack assembling process.

9.Others

9.1 Cell connection

- 1) Direct soldering of wire leads or devices to the cell is strictly prohibited.
- 2) Lead tabs with pre-soldered wiring shall be spot welded to the cells.

Direct soldering may cause damage of components, such as separator and insulator, by heat generation.

9.2 Prevention of short circuit within a battery pack

Enough insulation layers between wiring and the cells shall be used to maintain extra safety protection. The battery pack shall be structured with no short circuit within the battery pack, which may cause generation of smoke or firing.

9.3 Prohibition of disassembly

1) Never disassemble the cells

The disassembling may generate internal short circuit in the cell, which may cause gassing, firing, explosion, or other problems.

2) Electrolyte is harmful

LIP battery should not have liquid from electrolyte flowing, but in case the electrolyte come into contact with the skin, or eyes, physicians shall flush the electrolyte immediately with fresh water and medical advice is to be sought.



Ver:	Α	
DATE:	2019-03-22	
DOC N	o:JLD-105568P	

3) Prohibition of dumping of cells into fire

Never incinerate nor dispose the cells in fire. These may cause explosion of the cells, which is very dangerous and is prohibited.

9.5 Prohibition of cells immersion into liquid such as water

The cells shall never be soaked with liquids such as water, seawater, drinks such as soft drinks, juices, coffee or others.

9.6 Battery cells replacement

The battery replacement shall be done only by either cells supplier or device supplier and never be done by the user.

9.7 Prohibition of use of damaged cells

The cells might be damaged during shipping by shock. If any abnormal features of the cells are found such as damages in a plastic envelop of the cell, deformation of the cell package, smelling of an electrolyte, an electrolyte leakage and others, the cells shall never be used any more.

The Cells with a smell of the electrolyte or a leakage shall be placed away from fire to avoid firing or explosion.

10.Period of Warranty

The period of warranty is half a year from the date of shipment. Great Power guarantees to give a replacement in case of cells with defects proven due to manufacturing process instead of the customer abuse and misuse.

11. Storage of the Batteries

The batteries should be stored at room temperature, charged to about 30% to 50% of capacity. We recommend that batteries be charged about once per half a year to prevent over discharge.

12. Other The Chemical Reaction

Because batteries utilize a chemical reaction, battery performance will deteriorate over time even if stored for a long period of time without being used. In addition, if the various usage conditions such as charge, discharge, ambient temperature, etc. are not maintained within the specified ranges the life expectancy of the battery may be shortened or the device in which the battery is used may be damaged by electrolyte leakage. If the batteries cannot maintain a charge for long periods of time, even when they are charged correctly, this may indicate it is time to change the battery.

13. Note

Any other items which are not covered in this specification shall be agreed by both parties.




Ver:	Α
DATE:	2019-03-22

DOC No:JLD-105568P

Polarity

Connector Type: JST-PH (2mm Pitch)



Bottom of Connector